

**TAITALAC 8540T**

ABS

Taita Chemical Company, Ltd.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>5</b>	g/10min	ASTM D 1238
Temperature	<b>200</b>	°C	-
Load	<b>5</b>	kg	-
Mold Shrinkage, MD	<b>0.004</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>37.2</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>29.6</b>	MPa	ASTM D 638
Elongation at Break	<b>20</b>	%	ASTM D 638
Flexural Modulus	<b>2137</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 102</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>192</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ISO Data</b>			
Burning behav. 5V at thickness h	<b>5VA</b>	class	IEC 60695-11-20
Thickness tested	<b>3.2</b>	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Thickness tested	<b>1.59</b>	mm	-
DTUL @ 264 psi	<b>77</b>	°C	ASTM D 648
Vicat Temperature	<b>93.9</b>	°C	ASTM D 1525
<b>Other properties</b>			
Density	<b>1170</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Flame retardant

**Applications**

IT / Business Machine, Electrical and Electronical

**Regional Availability**

Asia Pacific