

Tarfuse® ABS PLUS 2 NAT

ABS

Grupa Azoty S.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	29	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Glass transition temperature, 10°C/min	103	°C	ISO 11357-1/-2

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ISO 1183

3D Data	Value	Unit	Test Standard
Tensile modulus, flat	2300	MPa	-
Yield stress, flat	38	MPa	-
Yield strain, flat	2.1	%	-
Stress at break, flat	33	MPa	-
Strain at break, flat	6.1	%	-

Characteristics**Processing**

Additive Manufacturing

Applications

Filament for 3D Printing

Delivery form

Natural Color

Regional Availability

Europe