

Tarodur 100

ABS

Taro Plast S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	2500	MPa	ISO 527
Yield stress	48	MPa	ISO 527
Strain at break	25	%	ISO 527
Flexural modulus, 23°C	2400	MPa	ISO 178
Charpy notched impact strength, +23°C	15	kJ/m ²	ISO 179/1eA
ASTM Data			
Izod Impact notched, 1/8 in	180	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	85	°C	ISO 75-1/-2
Vicat softening temperature, A	105	°C	ISO 306
Vicat softening temperature, B	95	°C	ISO 306
Coeff. of linear therm. expansion, parallel	90	E-6/K	ISO 11359-1/-2
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
Limiting Oxygen Index	21	%	ASTM D 2863
Electrical properties			
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Other properties			
Water absorption	0.15	%	Sim. to ISO 62
Density	1040	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Anti-static, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Features

Low Odor

Applications

Automotive, Electrical and Electronical, General Purpose

Regional Availability

Europe