

Techno ABS 150 (12A)

ABS

Techno-UMG Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	16	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	43	MPa	ISO 527
Flexural modulus, 23°C	2290	MPa	ISO 178
Flexural strength	69	MPa	ISO 178
Charpy impact strength, +23°C	26	kJ/m ²	ISO 179/1eU
Rockwell hardness	R 105	-	ISO 2039-2

ASTM Data			
Tensile Strength	43.1	MPa	ASTM D 638
Flexural Modulus	2350	MPa	ASTM D 790
Flexural Strength	73.5	MPa	ASTM D 790
Rockwell Hardness	R 106	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ISO 1183
Density	1040	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	2 - 5	h	-
Mold temperature	40 - 80	°C	-
Zone 1	190 - 260	°C	-

Characteristics**Processing**

Injection Molding

Applications

General Purpose

Special Characteristics

High impact or impact modified

Regional Availability

North America, Asia Pacific