

Techno ABS F1350 (D4)

ABS

Techno-UMG Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	23	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Strength	50	MPa	ISO 527
Flexural modulus, 23°C	2660	MPa	ISO 178
Flexural strength	79	MPa	ISO 178
Charpy impact strength, +23°C	13	kJ/m ²	ISO 179/1eU
Rockwell hardness	R 112	-	ISO 2039-2
Thermal properties			
ISO Data			
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	1.1	mm	-
Other properties			
Density	1090	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	2 - 5	h	-
Mold temperature	40 - 80	°C	-
Zone 1	180 - 230	°C	-

Characteristics**Processing**

Injection Molding

Features

Thermal Stability

Special Characteristics

Flame retardant, Light stabilized or stable to light

Regional Availability

North America, Asia Pacific