

Techno ABS F5330 (NC100)

ABS

Techno-UMG Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	9	g/10min	ISO 1133
Temperature	200	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Strength	42	MPa	ISO 527
Flexural modulus, 23°C	2160	MPa	ISO 178
Flexural strength	62	MPa	ISO 178
Charpy impact strength, +23°C	9	kJ/m ²	ISO 179/1eU
Rockwell hardness	R 102	-	ISO 2039-2
ASTM Data			
Tensile Strength	45.1	MPa	ASTM D 638
Flexural Modulus	2550	MPa	ASTM D 790
Flexural Strength	70.6	MPa	ASTM D 790
Rockwell Hardness	R 103	-	ASTM D 785
Thermal properties			
ISO Data			
Burning behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	2.5	mm	-
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.5	mm	-
Other properties			
Density	1210	kg/m ³	ISO 1183
Density	1210	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	2 - 5	h	-
Mold temperature	40 - 80	°C	-
Zone 1	180 - 210	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Asia Pacific

Special Characteristics

Flame retardant