

RTP 600 TFE 20

(ABS+PTFE)

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2206	MPa	ASTM D 638
Tensile Strength	37.9	MPa	ASTM D 638
Flexural Modulus	2275	MPa	ASTM D 790
Flexural Strength	68.6	MPa	ASTM D 790
Izod Impact notched, 1/8 in	64.1	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.59	mm	-

Other properties	Value	Unit	Test Standard
Density	1160	kg/m ³	ASTM D 792
Moisture Content	0.1	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	82.2	°C	-
Pre-drying - Time	2	h	-
Melt temperature	204 - 238	°C	-
Mold temperature	62.8 - 85	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Additives

Lubricants