

UMG Alloy® CG900S

ABS

Techno-UMG Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	7	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2050	MPa	ISO 527
Tensile Strength	50	MPa	ISO 527
Flexural modulus, 23°C	2150	MPa	ISO 178
Flexural strength	81	MPa	ISO 178
Charpy notched impact strength, +23°C	50	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	25	kJ/m ²	ISO 179/1eA
Rockwell hardness	R 108	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	71	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	85	E-6/K	ISO 11359-1/-2

Other properties	Value	Unit	Test Standard
Density	1150	kg/m ³	ISO 1183

Characteristics**Regional Availability**

Asia Pacific