

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	47	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Strength	51	MPa	ISO 527
Flexural modulus, 23°C	2500	MPa	ISO 178
Flexural strength	77	MPa	ISO 178
Charpy impact strength, +23°C	8	kJ/m ²	ISO 179/1eU
Rockwell hardness	R 110	-	ISO 2039-2
ASTM Data			
Tensile Strength	53.9	MPa	ASTM D 638
Flexural Modulus	2750	MPa	ASTM D 790
Flexural Strength	90.2	MPa	ASTM D 790
Rockwell Hardness	R 111	-	ASTM D 785
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Other properties			
Density	1050	kg/m ³	ISO 1183
Density	1050	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	2 - 5	h	-
Mold temperature	50 - 100	°C	-
Zone 1	190 - 260	°C	-

Characteristics

Processing

Injection Molding

Applications

Automotive

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America, Asia Pacific