

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	6.3	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	48	MPa	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178
Flexural strength	70	MPa	ISO 178
Charpy impact strength, +23°C	18	kJ/m ²	ISO 179/1eU
Rockwell hardness	R 104	-	ISO 2039-2

ASTM Data			
Tensile Strength	49	MPa	ASTM D 638
Flexural Modulus	2450	MPa	ASTM D 790
Flexural Strength	73.5	MPa	ASTM D 790
Rockwell Hardness	R 100	-	ASTM D 785

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ISO 1183
Density	1050	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	85 - 95	°C	-
Pre-drying - Time	2 - 5	h	-
Mold temperature	50 - 100	°C	-
Zone 1	220 - 270	°C	-

Characteristics

Processing

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Applications

Automotive

Regional Availability

North America, Asia Pacific