

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	32	cm ³ /10min	ISO 1133
Mechanical properties			
ISO Data			
Tensile Modulus	2600	MPa	ISO 527
Yield stress	63	MPa	ISO 527
Yield strain	4.5	%	ISO 527
Charpy impact strength, +23°C	20	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	2.6	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Glass transition temperature, 10°C/min	78	°C	ISO 11357-1/-2
Temp. of deflection under load, 0.45 MPa	75	°C	ISO 75-1/-2
Vicat softening temperature, B	80	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Electrical properties			
ISO Data			
Volume resistivity	1E14	Ohm*m	IEC 62631-3-1
Comparative tracking index	600	-	IEC 60112
Optical properties			
ISO Data			
Luminous transmittance	91	%	ISO 13468-1, -2
Other properties			
Water absorption	0.01	%	Sim. to ISO 62
Density	1010	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Melt temperature	190 - 250	°C	-
Mold temperature	40 - 70	°C	-
Feed temperature	<60	°C	-
Zone 1	190 - 220	°C	-
Zone 2	200 - 230	°C	-
Zone 3	210 - 240	°C	-
Zone 4	220 - 250	°C	-
Nozzle temperature	220 - 250	°C	-
Screw speed	50 - 200	rpm	-
Injection speed	50 - 150	mm/s	-
Injection pressure	50 - 110	MPa	-
Back pressure	≤15	MPa	-
Holding pressure	30 - 60	MPa	-
Maximum residence time	<15	min	-

Characteristics

Processing

Injection Molding

Special Characteristics

Transparent

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa