

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.002</b>	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>5490</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>75.8</b>	MPa	ASTM D 638
Elongation at Break	<b>1.5</b>	%	ASTM D 638
Flexural Modulus	<b>5170</b>	MPa	ASTM D 790
Flexural Strength	<b>121</b>	MPa	ASTM D 790
Izod Impact notched, 1/4 in	<b>43</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>104</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>98</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1120</b>	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Delivery form

Pellets

### Features

Copolymer

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa