

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	13	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
ASTM Data			
Melt Flow Index, MFI	13	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	97	°C	ISO 11357-1/-3
ASTM Data			
Melting Temperature	97	°C	ASTM D 3418
Vicat Temperature	58	°C	ASTM D 1525
Other properties			
Density	1020	kg/m ³	ISO 1183
Density	1020	kg/m ³	ASTM D 792

Characteristics

Processing

Blown Film Extrusion, Other Extrusion, Coating

Delivery form

Pellets

Features

Heat Sealable, Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa