

PP 7445L (EPC57MA)

E/P

Nizhnekamskneftekhim OAO

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	6	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Flexural Modulus	1250	MPa	ASTM D 790
Izod Impact notched, 1/8 in	72.1	J/m	ASTM D 256
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Compression Molding

Delivery form

Pellets

Special Characteristics

Anti-static

Features

Nucleated, Thermal Stability, Copolymer

Chemical Resistance

Oxidation Resistance

Regional Availability

Europe, Asia Pacific