

**PP 7540L (EPC31H)**

E/P

Nizhnekamskneftekhim OAO

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	6	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Flexural Modulus	1300	MPa	ASTM D 790
Izod Impact notched, 1/8 in	72.1	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Features**

Nucleated, Thermal Stability, Copolymer

**Chemical Resistance**

Oxidation Resistance

**Regional Availability**

Europe, Asia Pacific