

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	2	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melting Temperature	99	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	930	kg/m <sup>3</sup>	ASTM D 792

Film Properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Break, MD	31	MPa	ASTM D 882
Tensile Strength at Break, TD	27	MPa	ASTM D 882
Elongation at Break, MD	330	%	ASTM D 882
Elongation at Break, TD	660	%	ASTM D 882

## Characteristics

### Processing

Film Extrusion

### Special Characteristics

High impact or impact modified

### Features

Heat Sealable, Copolymer

### Certifications

Food contact

### Applications

Packaging

### Regional Availability

Europe, Asia Pacific, Near East/Africa