

EVA 3514 Film

EVAC

Sipchem

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.5	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	88	°C	ASTM D 3418
Vicat Temperature	64	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	933	kg/m ³	ASTM D 792

Film Properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break, MD	31	MPa	ASTM D 882
Tensile Strength at Break, TD	27	MPa	ASTM D 882
Elongation at Break, MD	300	%	ASTM D 882
Elongation at Break, TD	730	%	ASTM D 882

Characteristics**Special Characteristics**

High impact or impact modified, Transparent

Features

Heat Sealable, Copolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

Europe, Asia Pacific, Near East/Africa