

EVA 3522 Film

EVAC

Sipchem

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 3.5 | g/10min | ASTM D 1238 |
| Temperature | 190 | °C | - |
| Load | 2.16 | kg | - |

| Thermal properties | Value | Unit | Test Standard |
|---------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Melting Temperature | 80 | °C | ASTM D 3418 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 944 | kg/m ³ | ASTM D 792 |

| Film Properties | Value | Unit | Test Standard |
|-------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Strength at Break, MD | 33 | MPa | ASTM D 882 |
| Tensile Strength at Break, TD | 31 | MPa | ASTM D 882 |
| Elongation at Break, MD | 350 | % | ASTM D 882 |
| Elongation at Break, TD | 750 | % | ASTM D 882 |

Characteristics**Features**

Heat Sealable, Copolymer

Regional Availability

Europe, Asia Pacific, Near East/Africa