

**Product Texts**

For more detailed information, please read our or contact our representatives in your region.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>1.4</b>	g/10min	ASTM D 1238

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>37.9</b>	MPa	ASTM D 638
Elongation at Yield	<b>710</b>	%	ASTM D 638
Rockwell Hardness	<b>R120</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>96.1</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
DTUL @ 66 psi	<b>250</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>249</b>	°C	ASTM D 648
Melting Temperature	<b>252</b>	°C	ASTM D 3418

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>937</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America