

Product Texts

Zenite 5130L is a 30% glass-reinforced LCP resin with improved toughness

Flammability at thickness h (0.8 V-0 mm)

UL recognition (h)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.1	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	10000	MPa	ISO 527
^[C] Stress at break	145	MPa	ISO 527
^[C] Strain at break	3.5	%	ISO 527

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	320	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	275	°C	ISO 75-1/-2
^[C] Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 1MHz	3.3	-	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	80	E-4	IEC 62631-2-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1630	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Special Characteristics**

Flame retardant

Regional Availability

North America, Europe, Asia Pacific