

GLAMIDE® TY-102 ND

(PA*+TPE)

Toyobo Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0085	mm/mm	ASTM D 955

Mechanical properties	dry / cond	Unit	Test Standard
ASTM Data			
Tensile Strength	50 / 27	MPa	ASTM D 638
Flexural Modulus	2000 / 800	MPa	ASTM D 790
Flexural Strength	75 / 35	MPa	ASTM D 790
Rockwell Hardness	R 102 /	-	ASTM D 785
Taber Abrasion Resistance	8	mg/1000 cycles	ASTM D 1044
Izod Impact notched, 1/8 in	310 / N	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	150 / 180	J/m	ASTM D 256
Temperature	-40	°C	-

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Coefficient of Thermal Expansion, MD	87	E-6/K	ASTM D 696
DTUL @ 66 psi	150	°C	ASTM D 648
DTUL @ 264 psi	58	°C	ASTM D 648

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Comparative tracking index	600 / 600	-	IEC 60112
ASTM Data			
Dielectric Strength, Short Time	18 / 14	kV/mm	ASTM D 149
Volume Resistivity	1E15 / 1E12	Ohm*cm	ASTM D 257
Arc Resistance	125 / 108	s	ASTM D 495

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	1	%	ASTM D 570
Water Absorption, Equilibrium	2.9	%	ASTM D 570
Density	1090	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 120	°C	-
Pre-drying - Time	3 - 5	h	-
Melt temperature	245 - 285	°C	-
Mold temperature	50 - 80	°C	-
Injection pressure	30 - 40	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific