

**DAIAMID® L-GF30**

PA12

Daicel-Evonik Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	3	cm <sup>3</sup> /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	5500	MPa	ISO 527
Yield stress	110	MPa	ISO 527
Yield strain	5	%	ISO 527
Stress at break	110	MPa	ISO 527
Strain at break	6	%	ISO 527
Charpy impact strength, +23°C	75	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	95	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	24	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	22	kJ/m <sup>2</sup>	ISO 179/1eA
Rockwell hardness	R109	-	ISO 2039-2
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	178	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	170	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	175	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	70	E-6/K	ISO 11359-1/-2
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	44	kV/mm	IEC 60243-1
<b>Other properties</b>			
Water absorption	1	%	Sim. to ISO 62
Humidity absorption	0.5	%	Sim. to ISO 62
Density	1240	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America