

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0115	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	24.5	MPa	ASTM D 638
Elongation at Break	25	%	ASTM D 638
Flexural Modulus	758	MPa	ASTM D 790
Izod Impact notched, 1/8 in	110	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	119	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	4000	kg/m ³	ASTM D 792

Characteristics

Processing
Injection Molding

Delivery form
Pellets, Natural Color

Special Characteristics
High impact or impact modified

Chemical Resistance
Radiation Resistance

Applications
Medical, Sports Equipment

Regional Availability
North America, Europe, Asia Pacific, South and Central America, Near East/Africa