

Product Texts

Product-nomenclature: ISO 16396-PA12-IP,,EHL1,C22-004

Product Attributes

Highly flexible, High viscosity, Improved impact resistance, Improved heat resistance, Plasticised, Improved UV resistance (outdoor use)

Markets

Automotive
Air intake systems, Fuel systems
Industry & Consumer goods
Hydraulics & Pneumatics

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.9 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.2 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	- / 360	MPa	ISO 527
^[C] Yield stress	- / 25	MPa	ISO 527
^[C] Yield strain	- / 20	%	ISO 527
^[C] Nominal strain at break	- / >50	%	ISO 527
^[C] Charpy impact strength, +23°C	- / N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	- / N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	- / N	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	- / 10	kJ/m ²	ISO 179/1eA
^[C] Shore D hardness	63 / *	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	173 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	45 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	95 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	140 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	180 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	- / 1E11	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E12	Ohm	IEC 62631-3-2
^[C] Electric strength	- / 32	kV/mm	IEC 60243-1
^[C] Comparative tracking index	- / 600	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	1.4 / *	%	Sim. to ISO 62
^[C] Humidity absorption	0.7 / *	%	Sim. to ISO 62
^[C] Density	1020 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Other Extrusion

Delivery form

Granules, Black

Additives

Plasticizer

Special Characteristics

High impact or impact modified, Light stabilized or stable to light, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa