

**Product Texts**

Product-nomenclature: ISO 16396-PA12-IP,,EHL1,C22-002

**Product Attributes**

Highly flexible, High viscosity, Improved impact resistance, Improved heat resistance, Plasticised, Improved UV resistance (outdoor use)

**Markets**

**Automotive**  
Compressed air systems, Fuel systems  
**Industry & Consumer goods**  
Hydraulics & Pneumatics

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	- / <b>250</b>	MPa	ISO 527
<sup>[C]</sup> Yield stress	- / <b>20</b>	MPa	ISO 527
<sup>[C]</sup> Yield strain	- / <b>45</b>	%	ISO 527
<sup>[C]</sup> Nominal strain at break	- / <b>&gt;50</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	- / <b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	- / <b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	- / <b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	- / <b>13</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>173 / *</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>40 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>50 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	<b>160 / *</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	<b>200 / *</b>	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	- / <b>1E11</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>* / 1E12</b>	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	- / <b>32</b>	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	- / <b>600</b>	-	IEC 60112

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Water absorption	<b>1.4 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>0.7 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1000 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Profile Extrusion, Other Extrusion

**Delivery form**

Granules, Natural Color

**Special Characteristics**

High impact or impact modified, Light stabilized or stable to light, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

**Additives**

Plasticizer

**Applications**

Automotive

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa