

**Product Texts**

Product-nomenclature: ISO 16396-PA12,,EHL,C18-020

**Product Attributes**

Improved heat resistance

**Markets**

**Automotive**

Hydraulic systems, Fuel systems

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	<b>0.8 / *</b>	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	<b>0.8 / *</b>	%	ISO 294-4, 2577

[C]: CAMPUS

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>1600 / 1200</b>	MPa	ISO 527
<sup>[C]</sup> Yield stress	<b>50 / 40</b>	MPa	ISO 527
<sup>[C]</sup> Yield strain	<b>5 / 10</b>	%	ISO 527
<sup>[C]</sup> Nominal strain at break	<b>&gt;50 / &gt;50</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>N / N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	<b>N / N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>6 / 7</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	<b>6 / 6</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Shore D hardness	<b>75 / *</b>	-	ISO 7619-1

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>178 / *</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>50 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>115 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	<b>120 / *</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	<b>140 / *</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at thickness h	<b>HB / *</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / *</b>	mm	-

[C]: CAMPUS

<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	<b>1E11 / 1E11</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>* / 1E12</b>	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	<b>36 / 35</b>	kV/mm	IEC 60243-1

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Water absorption	<b>1.5 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>0.7 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1010 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Film Extrusion, Other Extrusion

**Delivery form**

Natural Color

**Special Characteristics**

Light stabilized or stable to light, Heat stabilized or stable to heat

**Applications**

Automotive

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa