

Revolve® Explore CT PA

PA12

Matrix Polymers

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	31	MPa	ISO 527
Flexural modulus, 23°C	1250	MPa	ISO 178
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	80	°C	ISO 75-1/-2
Other properties			
Density	1010	kg/m ³	ISO 1183

Characteristics**Processing**

Rotational Molding

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Powder, Black, Natural Color

Regional Availability

Europe, Asia Pacific