

**Ubesta 3030 JFX3**

PA12

UBE

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	235	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577
Molding shrinkage, normal	1.3	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	25	MPa	ISO 527
Yield strain	26	%	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	400	MPa	ISO 178
Charpy notched impact strength, +23°C	115 <sup>[P]</sup>	kJ/m <sup>2</sup>	ISO 179/1eA
Shore D hardness	70	-	ISO 7619-1
Rockwell hardness	R 60	-	ISO 2039-2

P:

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	173	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	45	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	85	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	170	E-6/K	ISO 11359-1/-2

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E10	Ohm*m	IEC 62631-3-1

Other properties	Value	Unit	Test Standard
Density	1010	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Other Extrusion

**Delivery form**

Natural Color

**Additives**

Plasticizer

**Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

Europe