

**Ubesta 3030 JI12L**

PA12

UBE

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	2	g/10min	ISO 1133
Temperature	235	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Molding shrinkage, normal	1.9	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	28	MPa	ISO 527
Yield strain	18	%	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	500	MPa	ISO 178
Charpy notched impact strength, +23°C	110 <sup>[P]</sup>	kJ/m <sup>2</sup>	ISO 179/1eA
Shore D hardness	68	-	ISO 7619-1
Rockwell hardness	R 61	-	ISO 2039-2

P:

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	176	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	42	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	80	°C	ISO 75-1/-2

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1

Other properties	Value	Unit	Test Standard
Density	1000	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Other Extrusion

**Delivery form**

Black

**Additives**

Plasticizer

**Special Characteristics**

High impact or impact modified, U.V. stabilized or stable to weather

**Regional Availability**

North America, Europe