

Ubesta 3035 JU5

PA12

UBE

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	14	g/10min	ISO 1133
Temperature	235	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577
Molding shrinkage, normal	1.2	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	30	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	200	MPa	ISO 178
Charpy notched impact strength, +23°C	N	kJ/m ²	ISO 179/1eA
Shore D hardness	59	-	ISO 7619-1
Rockwell hardness	R 28	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	162	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	40	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	70	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	200	E-6/K	ISO 11359-1/-2

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E8	Ohm*m	IEC 62631-3-1

Other properties	Value	Unit	Test Standard
Density	1030	kg/m ³	ISO 1183

Characteristics**Processing**

Other Extrusion

Delivery form

Natural Color

Additives

Plasticizer

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe