

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	20500	MPa	ISO 527
Stress at break	165	MPa	ISO 527
Strain at break	2.6	%	ISO 527
Flexural modulus, 23°C	17500	MPa	ISO 178
Flexural strength	255	MPa	ISO 178
Izod impact strength, +23°C	56	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	16	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	170	°C	ISO 75-1/-2
Temp. of deflection under load, 8.00 MPa	130	°C	ISO 75-1/-2
Vicat softening temperature, B	170	°C	ISO 306

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	0.005	Ohm*m	IEC 62631-3-1
Surface resistivity	500	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1220	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	6 - 8	h	-
Melt temperature	250 - 265	°C	-
Mold temperature	110	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe