

Product Texts

Product-Nomenclature: ISO 16396-PA12 X,GB50,M1H,C18-040

Product Attributes

Hydrolysis resistant, Improved heat resistance

Markets

Industry & Consumer goods

Sanitary, water and gas supply

Approvals

Food Contact

EU Requirements, FDA

Potable Water Contact

NSF 61, KTW, WRAS, ACS, DVGW W270

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.6 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.6 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3700 / 3500	MPa	ISO 527
^[C] Stress at break	50 / 50	MPa	ISO 527
^[C] Strain at break	10 / 10	%	ISO 527
^[C] Charpy impact strength, +23°C	65 / 60	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	40 / 40	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	5 / 4	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	4 / 4	kJ/m ²	ISO 179/1eA
^[C] Shore D hardness	84 / *	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	178 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	80 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 8.00 MPa	50 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	70 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	70 / *	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E9 / 1E9	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2
^[C] Electric strength	35 / 35	kV/mm	IEC 60243-1
^[C] Comparative tracking index	- / 600	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	1.1 / *	%	Sim. to ISO 62
^[C] Humidity absorption	0.5 / *	%	Sim. to ISO 62
^[C] Density	1490 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Granules, Natural Color

Special Characteristics

Light stabilized or stable to light, Heat stabilized or stable to heat

Chemical Resistance

Hydrolytically Stable

Certifications

Food contact, Food approval FDA 21 CFR, Drinking water contact, Drinking water contact KTW, Drinking water contact DVGW W270, Drinking water contact NSF 61

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa