

Ecomass® Compound 1050ZB92

PA12-MED(x)

DOMO Engineering Plastics

Product Texts

Nontoxic alternative to Lead (Pb)

Processing/Physical Characteristics

	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955

Mechanical properties

	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	6205	MPa	ASTM D 638
Tensile Strength	44.8	MPa	ASTM D 638
Elongation at Break	1.75	%	ASTM D 638
Flexural Modulus	4964	MPa	ASTM D 790
Flexural Strength	48.3	MPa	ASTM D 790
Izod Impact notched, 1/8 in	112	J/m	ASTM D 256

Thermal properties

	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	121	°C	ASTM D 648
DTUL @ 264 psi	107	°C	ASTM D 648

Other properties

	Value	Unit	Test Standard
Density	6900	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding

	Value	Unit	Test Standard
Pre-drying - Temperature	73.9	°C	-
Pre-drying - Time	4	h	-
Melt temperature	232 - 260	°C	-
Mold temperature	65.6 - 82.2	°C	-

Characteristics**Processing**

Injection Molding

Chemical Resistance

Radiation Resistance

Delivery form

Pellets

Regional Availability

North America

Features

EMI Attenuation/Shielding, Low Odor, Copolymer