

**AKROMID® B3 GF 30 1 L natural (4684)**

(PA6+PP)-GF30

Akro-Plastic GmbH

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt volume-flow rate, MVR	<b>14 / *</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>275 / *</b>	°C	-
Load	<b>5 / *</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>8500 / 6500</b>	MPa	ISO 527
Stress at break	<b>150 / 100</b>	MPa	ISO 527
Strain at break	<b>3.2 / 3.7</b>	%	ISO 527
Flexural modulus, 23°C	<b>8800 / 6500</b>	MPa	ISO 178
Flexural strength	<b>210 / 150</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>70 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>17 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>220 / *</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>203 / *</b>	°C	ISO 75-1/-2
Burning behav. at thickness h	<b>HB / *</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / *</b>	mm	-
<b>Other properties</b>			
Density	<b>1260 / -</b>	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Melt temperature	<b>270</b>	°C	-
Mold temperature	<b>80</b>	°C	-
Injection pressure	<b>75</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Natural Color

**Special Characteristics**

Heat stabilized or stable to heat

**Applications**

Automotive, Electrical and Electronical

**Regional Availability**

Europe, Asia Pacific