

CELANYL® B3 W MGF2515 NC 1102/1A

PA6-(MD+GF)

Celanese

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	199	°C	ISO 75-1/-2
[C]: CAMPUS			

Other properties	Value	Unit	Test Standard
^[C] Density	1480	kg/m ³	ISO 1183
[C]: CAMPUS			

Characteristics**Delivery form**

Natural Color