

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	29000	MPa	ISO 527
^[C] Stress at break	310	MPa	ISO 527
^[C] Strain at break	1.3	%	ISO 527
^[C] Charpy impact strength, +23°C	73	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	26	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1310	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Special Characteristics

Increased electrical conductivity

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific