

**Product Texts**

**High viscosity, self-extinguishing PA12 compound, free of halogen and phosphorus**

**VESTAMID® X7229 NC** is a heat-stabilized and plasticized PA 12 compound containing a non-migrating flame retardant, free of halogen and phosphorus. VESTAMID® X7229 NC complies with the requirements of FAR 25.853 or ABD 0031.

Due to the halogen- and phosphorus-free flame retardants, VESTAMID® X7229 NC is especially suitable for interior parts in aircrafts, railway vehicles and ships. It can be used for extrusion as well as for injection molding.

Due to the flame retardants, melt temperature should not exceed 260°C. We recommend melt temperatures of 210-230°C.

VESTAMID® X7229 NC is supplied as cylindrical pellets ready for processing in moisture-proof bags.

The use of colorants may affect property values.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

For information about processing of VESTAMID®, please follow the general commendations about [“Processing of VESTAMID® compounds”](#).

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT [EVONIK-HP@EVONIK.COM](mailto:EVONIK-HP@EVONIK.COM) OR VISIT OUR PRODUCT AT [WWW.VESTAMID.COM](http://WWW.VESTAMID.COM)

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	<b>26 / *</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>220 / *</b>	°C	-
Load	<b>10 / *</b>	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	<b>0.6 / *</b>	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	<b>0.8 / *</b>	%	ISO 294-4, 2577

[C]: CAMPUS

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>980 / -</b>	MPa	ISO 527
<sup>[C]</sup> Yield stress	<b>36 / -</b>	MPa	ISO 527
<sup>[C]</sup> Yield strain	<b>17 / -</b>	%	ISO 527
<sup>[C]</sup> Nominal strain at break	<b>&gt;50 / -</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>N / -</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	<b>N / -</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>11 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Type of failure	<b>C / -</b>	-	-
<sup>[C]</sup> Charpy notched impact strength, -30°C	<b>5 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Type of failure	<b>C / -</b>	-	-

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>175 / *</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>40 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>130 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	<b>150 / *</b>	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	<b>80 / *</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	<b>V-2 / *</b>	class	IEC 60695-11-10
Thickness tested	<b>1.6 / *</b>	mm	-

[C] Burning Behav. at thickness h	<b>V-2 / *</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / *</b>	mm	-
[C] Oxygen index	<b>24 / *</b>	%	ISO 4589-1/-2

[C]: CAMPUS

<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
[C] Relative permittivity, 1MHz	<b>5 / -</b>	-	IEC 62631-2-1
[C] Dissipation factor, 1MHz	<b>1700 / -</b>	E-4	IEC 62631-2-1
[C] Volume resistivity	<b>1E11 / -</b>	Ohm*m	IEC 62631-3-1
[C] Comparative tracking index	<b>600 / -</b>	-	IEC 60112

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
[C] Water absorption	<b>1.4 / *</b>	%	Sim. to ISO 62
[C] Humidity absorption	<b>0.6 / *</b>	%	Sim. to ISO 62
[C] Density	<b>1060 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

<b>Test specimen production</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
[C] Injection Molding, melt temperature	<b>220</b>	°C	ISO 294
Injection Molding, mold temperature	<b>80</b>	°C	ISO 294
Injection Molding, injection velocity	<b>200</b>	mm/s	ISO 294
Injection Molding, pressure at hold	<b>70</b>	MPa	ISO 294

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding, Profile Extrusion, Other Extrusion

**Delivery form**

Pellets, Natural Color

**Additives**

Plasticizer

**Special Characteristics**

Flame retardant, Halogen-free, Phosphorus-free, Heat stabilized or stable to heat

**Applications**

Aircraft and Aerospace

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa