

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	287 / *	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	75 / *	°C	ISO 11357-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	13 / *	%	Sim. to ISO 62
^[C] Humidity absorption	3.7 / *	%	Sim. to ISO 62
^[C] Density	1180 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Other Extrusion

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets