

Titalon 4300CF

PA46-CF30

Titan Plastics Compounds Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	260	MPa	ISO 527
Flexural modulus, 23°C	17200	MPa	ISO 178
Flexural strength	360	MPa	ISO 178
Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	300	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Electrical properties			
ISO Data			
Volume resistivity	1	Ohm*m	IEC 62631-3-1
Surface resistivity	100	Ohm	IEC 62631-3-2
Other properties			
Density	1330	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	4	h	-
Melt temperature	290 - 320	°C	-
Mold temperature	80 - 120	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Black

Special Characteristics

Increased electrical conductivity

Regional Availability

Asia Pacific