

**Product Texts**

30% Glass Reinforced, Heat Stabilized

ISO 1043 PA46-GF30

Stanyl® TW200F6 is a high heat polyamide that offers excellent creep resistance, strength, stiffness and fatigue resistance, not only at ambient temperatures but especially at high temperatures, while at the same time providing cycle-time advantages and excellent flow.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Density of melt	1210	kg/m <sup>3</sup>	-
<sup>[C]</sup> Thermal conductivity of melt	0.296	W/(m K)	-
<sup>[C]</sup> Spec. heat capacity of melt	2200	J/(kg K)	-
<sup>[C]</sup> Eff. thermal diffusivity	1.1E-7	m <sup>2</sup> /s	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	10000 / 6000	MPa	ISO 527
<sup>[C]</sup> Stress at break	210 / 115	MPa	ISO 527
<sup>[C]</sup> Strain at break	3.7 / 6	%	ISO 527
<sup>[C]</sup> Tensile creep modulus, 1000h	* / 4500	MPa	ISO 899-1
<sup>[C]</sup> Charpy impact strength, +23°C	80 / 100	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	65 / 75	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	12 / 21	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	11 / 11	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	295 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	75 / *	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	290 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	290 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	290 / *	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	25 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	60 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
Yellow Card available	yes / *	-	-
<sup>[C]</sup> Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	3.0 / *	mm	-
Yellow Card available	yes / *	-	-
<sup>[C]</sup> Burning rate, FMVSS, Thickness 1 mm	55	mm/min	ISO 3795 (FMVSS 302)
<sup>[C]</sup> Oxygen index	22 / *	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	4.3 / 16	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	4 / 4.7	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	70 / 6000	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	200 / 1000	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	1E12 / 1E7	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	30 / 20	kV/mm	IEC 60243-1

[C] Comparative tracking index	300 / -	-	IEC 60112
--------------------------------	---------	---	-----------

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
[C] Water absorption	9.5 / *	%	Sim. to ISO 62
[C] Humidity absorption	2.6 / *	%	Sim. to ISO 62
[C] Density	1410 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
[C] Viscosity number	145 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

[C]: CAMPUS

## Characteristics

### Processing

Injection Molding

### Special Characteristics

Platable, Heat stabilized or stable to heat

### Delivery form

Pellets

### Regional Availability

North America, Europe, Asia Pacific

## Other text information

### Injection molding

[Injection Molding Recommendations](#)
[Hot runner recommendations for molding high heat performance Engineering Materials](#)
[Steel recommendations for molds screws and barrels](#)
[Supporting document for Stanyl quality processing](#)
[Trouble shooting guideline for injection molding](#)