

Product Texts

40% Glass Reinforced, Heat Stabilized, High Flow, for E&E applications

ISO 1043 PA46-GF40

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	13500 / 9000	MPa	ISO 527
^[C] Stress at break	210 / 150	MPa	ISO 527
^[C] Strain at break	2.2 / 3.1	%	ISO 527
^[C] Charpy impact strength, +23°C	70 / 95	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	60 / 60	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	12 / 15	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	12 / 12	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	295 / *	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	75 / *	°C	ISO 11357-1/-2
^[C] Temp. of deflection under load, 1.80 MPa	290 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	290 / *	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	290 / *	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	15 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	140 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
Yellow Card available	yes / *	-	-
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	3.0 / *	mm	-
Yellow Card available	yes / *	-	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / 1E9	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E14	Ohm	IEC 62631-3-2
^[C] Electric strength	30 / 25	kV/mm	IEC 60243-1
^[C] Comparative tracking index	475 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	8.1 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2.2 / *	%	Sim. to ISO 62
^[C] Density	1510 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Viscosity number	80 / *	cm ³ /g	ISO 307, 1157, 1628

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Applications

Electrical and Electronical

Stanyl® 46HF4540

PA46-GF40

Envalior

Delivery form

Pellets

Regional Availability

North America, Asia Pacific

Special Characteristics

Heat stabilized or stable to heat

Other text information

Injection molding

[Injection Molding Recommendations](#)

[Hot runner recommendations for molding high heat performance Engineering Materials](#)

[Steel recommendations for molds screws and barrels](#)

[Supporting document for Stanyl quality processing](#)

[Trouble shooting guideline for injection molding](#)