

Product Texts

Heat Stabilized, Impact Modified

ISO 1043 PA46-I

Stanyl® TW363 is an impact-modified high heat polyamide that offers excellent wear & friction properties in combination with outstanding creep resistance, strength, stiffness and fatigue resistance especially at high temperatures in combination with cycle-time advantages and excellent flow.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Density of melt	913	kg/m ³	-
^[C] Thermal conductivity of melt	0.24	W/(m K)	-
^[C] Spec. heat capacity of melt	2550	J/(kg K)	-
^[C] Eff. thermal diffusivity	9.82E-7	m ² /s	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	1850 / 600	MPa	ISO 527
^[C] Yield stress	60 / 45	MPa	ISO 527
^[C] Yield strain	20 / 25	%	ISO 527
^[C] Nominal strain at break	>50 / >50	%	ISO 527
^[C] Charpy impact strength, +23°C	N / N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	N / N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	75 / 125	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	26 / 30	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	295 / *	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	75 / *	°C	ISO 11357-1/-2
^[C] Temp. of deflection under load, 1.80 MPa	90 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	200 / *	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	250 / *	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	160 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	180 / *	E-6/K	ISO 11359-1/-2
^[C] Oxygen index	27 / *	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	3.6 / 14	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	3.2 / 4	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	120 / 6500	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	190 / 1000	E-4	IEC 62631-2-1
^[C] Volume resistivity	1E13 / 1E7	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2
^[C] Electric strength	25 / 15	kV/mm	IEC 60243-1
^[C] Comparative tracking index	475 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	11 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2.95 / *	%	Sim. to ISO 62

[C] Density

1100 / -kg/m³

ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding, Profile Extrusion, Other Extrusion

Delivery form

Pellets

Special Characteristics

Platable, High impact or impact modified, Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific

Other text information**Injection molding**[Injection Molding Recommendations](#)[Hot runner recommendations for molding high heat performance Engineering Materials](#)[Steel recommendations for molds screws and barrels](#)[Supporting document for Stanyl quality processing](#)[Trouble shooting guideline for injection molding](#)