

Product Texts

Product-nomenclature: ISO 16396-PA6,GF30 X,M1HRZ,S14-090N

Product Attributes

Anti-static

Markets

Automotive

Automotive electr. and electronics, lighting

Electricals & Electronics

Connectors

Industry & Consumer goods

Housewares, Mechanical Engineering, Power transmission, Sports & Leisure, Tools & Accessories

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.1 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.7 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9400 / 5000	MPa	ISO 527
^[C] Stress at break	100 / 80	MPa	ISO 527
^[C] Strain at break	6 / 10	%	ISO 527
^[C] Charpy impact strength, +23°C	50 / 60	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	30 / 30	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	8 / 10	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	7 / 7	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	205 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	100 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	25 / -	Ohm*m	IEC 62631-3-1

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	7 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2 / *	%	Sim. to ISO 62
^[C] Density	1620 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Grilon BG-30 EC natural

PA6-GF15

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Processing

Injection Molding

Delivery form

Granules, Natural Color

Special Characteristics

Anti-static

Applications

Automotive, Electrical and Electronical, Sports Equipment

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa