

Product Texts

For gas assisted injection technology.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	83	MPa	ASTM D 638
Elongation at Break	13	%	ASTM D 638
Flexural Modulus	3790	MPa	ASTM D 790
Flexural Strength	145	MPa	ASTM D 790
Izod Impact notched, 1/8 in	48	J/m	ASTM D 256
Thermal properties			
ASTM Data	Value	Unit	Test Standard
Melting Temperature	220	°C	ASTM D 3418
Other properties			
Value	Unit	Test Standard	
Density	1230	kg/m ³	ASTM D 792

Characteristics**Certifications**

RoHS compliant

Regional Availability

Europe, Asia Pacific