

**MAPEX® AN0320SN B01**

PA6-GF15

Ginar Technology Co.,Ltd.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.004</b>	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>110</b>	MPa	ASTM D 638
Elongation at Break	<b>4</b>	%	ASTM D 638
Flexural Modulus	<b>5169</b>	MPa	ASTM D 790
Flexural Strength	<b>183</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 120</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>64</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 264 psi	<b>210</b>	°C	ASTM D 648
Melting Temperature	<b>220</b>	°C	ASTM D 3418

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Dielectric Strength, Short Time	<b>16.5</b>	kV/mm	ASTM D 149

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Water Absorption, 24hr	<b>0.3</b>	%	ASTM D 570
Density	<b>1220</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Delivery form**

Black

**Regional Availability**

Europe, Asia Pacific

**Certifications**

RoHS compliant