

Product Texts

Medium viscosity Polyamide 6, 15% glassfiber reinforced.
For moulding parts with increased stiffness.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	5400	MPa	ISO 527
Stress at break	120	MPa	ISO 527
Strain at break	2	%	ISO 527
Charpy impact strength, +23°C	40	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	185	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	201	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Other properties	Value	Unit	Test Standard
Water absorption	7.9	%	Sim. to ISO 62
Humidity absorption	2.5	%	Sim. to ISO 62
Density	1220	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 8	h	-
Processing humidity	≤0.1	%	-
Mold temperature	40 - 80	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	240 - 260	°C	-
Nozzle temperature	250 - 270	°C	-
Maximum residence time	10	min	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Regional Availability

Europe