

**Product Texts**

Base Polymer	Polyamide 6
Filler/Additive System	20 % glass fibres
Special Features	heat stabilised, fast solidifying
Market Segment	various
Application Area	various

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>6700 / -</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>140 / -</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>3.3 / -</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>50 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>7.5 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>207 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Burning Behav. at thickness h	<b>HB / *</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / *</b>	mm	-
Yellow Card available	<b>yes / *</b>	-	-

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>1270 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Other text information****Injection molding**

Pre-Drying Conditions      in a dry air (desiccant) dryer <80 °C  
for 2-12 h  
dependant on moisture content

Processing Injection Moulding      melt temperature 270-290 °C  
mould temperature 80-100 °C

Storage      dry, protected from light