

N5120S-NAD

PA6-GF20

Pontex Polyblend Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.22	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	78.5	MPa	ASTM D 638
Flexural Modulus	4611	MPa	ASTM D 790
Flexural Strength	147	MPa	ASTM D 790
Izod Impact notched, 1/8 in	147	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	180	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1250	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

Asia Pacific