

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>117</b>	MPa	ASTM D 638
Flexural Modulus	<b>4619</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>53.4</b>	J/m	ASTM D 256

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>66 - 82</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Processing humidity	<b>≤0.2</b>	%	-
Melt temperature	<b>288 - 302</b>	°C	-
Mold temperature	<b>49 - 93</b>	°C	-
Zone 1	<b>249 - 277</b>	°C	-
Zone 2	<b>260 - 288</b>	°C	-
Zone 3	<b>271 - 299</b>	°C	-
Nozzle temperature	<b>271 - 299</b>	°C	-
Injection pressure	<b>8 - 18</b>	MPa	-
Back pressure	<b>0 - 50</b>	MPa	-
Holding pressure	<b>6 - 15</b>	MPa	-
Maximum residence time	<b>6</b>	min	-

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

High impact or impact modified

**Delivery form**

Black

**Regional Availability**

North America