

AKROMID® B3 GF 25 FRT natural (6910)

PA6-GF25

Akro-Plastic GmbH

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7 / *	%	ISO 294-4, 2577

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	10000 / 5500	MPa	ISO 527
Stress at break	130 / 90	MPa	ISO 527
Strain at break	3 / 7	%	ISO 527
Charpy impact strength, +23°C	70 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	11 / 16	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
Burning behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Burning behav. at thickness h	V-1 / *	class	IEC 60695-11-10
Thickness tested	0.4 / *	mm	-
Oxygen index	32 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	0.4	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (2)	0.8	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (3)	1.6	mm	-

Other properties	dry / cond	Unit	Test Standard
Density	1370 / -	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	270	°C	-
Mold temperature	80	°C	-
Injection pressure	75	MPa	-

Characteristics**Processing**

Injection Molding

Certifications

RoHS compliant

Delivery form

Natural Color

Regional Availability

Europe, Asia Pacific

Special Characteristics

Flame retardant, Halogen-free